

MISTERO SERIES



WHITE HORSE CERAMIC INDUSTRIES (VIETNAM) CO.,LTD



PORCELAIN STONE TILE
300mm x 600mm



HE36043


MISTERO SERIES

300mm x 600mm 12" x 24"


M Matt Finish **S** Structure Finish, Glazed



HE36044




Porcelain



Floor



Wall



V2

Variation

There is nothing more breathtaking and awe-inspiring than watching the setting sun stealthily sinking into the vast MISTERO.

And there is nothing more astounding than to manifest their majestic color into the very threshold of your home.

Không có gì ngoạn mục và đáng kinh ngạc hơn là được ngắm mặt trời lặn một cách thẹn thùng hòa mình vào MISTERO rộng lớn

Và không có gì ngạc nhiên hơn là thể hiện được màu sắc tinh tế của chúng vào ngưỡng cửa nhà bạn.



Porcelain



Floor



Wall



V2

Variation

MISTERO SERIES

300mm x 600mm 12" x 24"

M Matt Finish S Structure Finish, Glazed



HE36044

MISTERO SERIES

300mm x 600mm 12" x 24"

M Matt Finish **S** Structure Finish, Glazed



HE36043



HE36044

TEST REPORT

DIMENSIONS AND SURFACE QUALITY	PORCELAIN TILES - GROUP B1a		PHYSICAL PROPERTIES	PORCELAIN TILES - GROUP B1a		CHEMICAL PROPERTIES	PORCELAIN TILES - GROUP B1a	
	ISO 10545 Standard	White Horse Tiles (Test Result By SIRIM)		ISO 10545 Standard	White Horse Tiles (Test Result By SIRIM)		ISO 10545 Standard	White Horse Tiles (Test Result By SIRIM)
Length and Width	± 0.6%	Passed	Water Absorption	Maximum 0.5%	Average 0.07% Individual Maximum 0.10%	Chemical Resistance To Household Chemical Of Glazed Tiles	Minimum GB	No Visible Effect (GA)
Thickness	± 0.5%	Passed	Breaking Strength	Not Less Than 1300N	Average 2000N	Chemical Resistance To Swimming Pool Salts Of Glazed Tiles	Minimum GB	No Visible Effect (GA)
Straightness of Sides	± 0.5%	Passed	Modulus of Rupture	Minimum 35N/mm ²	Average 63N/mm ² Individual Minimum 56N/mm ²	Chemical Resistance To Hydrochloric Acid (3%) Of Glazed Tiles	GLA: No Visible Effect	GLA
Rectangularity	± 0.6%	Passed	Resistance to Deep Abrasion of Unglazed Tiles	Maximum 175mm ³	126mm ³	Chemical Resistance To Citric Acid (100g/l) Of Glazed Tiles	GLB: Definite Change In Appearance	GLA
Flatness of Surface	± 0.5%	Passed	Resistance to Surface Abrasion of Glazed Tiles	Class3: For Normal Footwear Class4: For Regular Traffic With Some Scratching Dirt	Class4	Chemical Resistance To Potassium Hydroxide (30g/l) Of Glazed Tiles	GLC: Partial Or Complete Loss Of The Original Surface	GLA
Centre Curvature	± 0.5%	Passed						
Edge Curvature	± 0.5%	Passed						
Warpage	± 0.5%	Passed						
Surface Quality	A Minimum of 100% free from visible defects	Passed	Crazing Resistance	No Crazing Observed	Pass	Staining Resistance Test Of Glazed Tiles	Minimum Class 3	Class5 (Stain Can Be Easily Removed With Running Hot Water)

MAIN OFFICE:

2A Street, My Xuan A industries, My Xuan Ward
Phu My Town, Ba Ria - Vung Tau Province
Tel: 84 0254 393 2333
Fax: 84 0254 393 2338

CAN THO BRANCH

225 Street 3/2, Hung Loi Ward
Ninh Kieu District, Can Tho City
Tel: 84 0292 383 9999
Fax: 84 0292 383 1111

HAI PHONG BRANCH

750 Nguyen Van Linh Street,
Le Chan District, Hai Phong City
Tel: 84 0225 378 4555
Fax: 84 0225 378 4666

HO CHI MINH BRANCH

270A Ly Thuong Kiet Street, 10 District
Ho Chi Minh City
Tel: 84 0283 3864 9800
Fax: 84 0283 3864 9808

DA NANG BRANCH

Lot 48, No.4 Street, An Don - Da Nang Industries
Son Tra District, Da Nang City
Tel: 84 0236 393 1222
Fax: 84 0236 393 1228

HA NOI BRANCH

Ha Noi shipping Factory, Thanh Tri Ward
Hoang Mai District, Ha Noi City
Tel: 84 0243 3644 6555
Fax: 84 0243 3644 6553

NHA TRANG BRANCH

No.131B Street 23/10, Phuong Son Ward
Khanh Hoa Province, Nha Trang City
Tel: 84 0258 3821 085
Fax: 84 0258 3821 086

WHITE HORSE CERAMIC INDUSTRIES (VIET NAM) CO.LTD

Email: cshq@whitehorse.vn
whvn@vnn.vn
Website: www.whitehorse.vn

SHADE & TONALITIES

V1 UNIFORM
FROM TILE TO TILE

V1
Colour range and tonality within the same shade is fairly uniform from tile to tile.
Minimal to zero difference among tiles from the same production run.

V2 SLIGHTLY NOTICEABLE
FROM TILE TO TILE

V2
Colour range and tonality within the same shade is slightly noticeable from tile to tile.
Visibly distinguished difference in design or pattern with minimal change in colour tones.

V3 MODERATELY NOTICEABLE
FROM TILE TO TILE

V3
Colour range and tonality within the same shade is moderately noticeable from tile to tile.
Visibly distinguished difference in design or pattern.

V4 DISTINCTLY NOTICEABLE
FROM TILE TO TILE

V4
Colour range and tonality within the same shade is distinctly noticeable from tile to tile.
Random colour differences from tile to tile create the possibility of unique tile compositions.

SIZE	CARTON		PALLET	
	Pcs/Ctn	Pallet	M2/Ctn	M2/Pallet
30 cm x 60 cm	8	72	1.44	103.68